

Product data sheet

COLETANCHE XP4

Description

Coletanche XP4 is an elastomeric modified bituminous geomembrane.

Use

Extreme level of mechanical constraints, exposed or covered (aggressive materials, reinforced precautions). For example:

- Storage of harmful waste,
- Large dams,
- Railways (use directly under ballast),
- Railway bridges.

The product use must be validated by consultation.

Application method

By torch welding or other similar process.

Storage

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 35 cm to be placed under the ends of the mandrel.

Composition (indicative)

Reinforcement:	Geotextile	300 g/m ²
Reinforcement:		-
Binder:	Elastomeric bitumen	5000 g/m ²
Surface finish:	Sand	250 g/m ²
Underside finish:	Silicone coated film	15 g/m ²

Characteristics

		Standards	Units	Average	Minimum
Dimensions	Length	EN 1868-1	m	65	64
	Width		m	5,10	5,01
Thickness (on finished product)		EN 1869-1	mm	4,20	4,00
Surface mass		EN 1869-1	kg/m ²	5,50	5,10
Tensile properties: Strength	Longitudinal direction	EN 12311-1	N/50 mm	1550	1200
	Cross direction			1250	1000
Tensile properties: Elongation	Longitudinal direction		%	35	25
	Cross direction			35	25
Flexibility at low temperature		EN 1109	°C	-20	-16
Static puncture	Resistance	EN ISO 12236	kN	4	3,5
	Displacement		mm	50	40
Water permeability		EN 14150	m ³ /m ² /d	1.10 ⁻⁶	<
Gas permeability		ASTM D1434-82	m ³ /(m ² .d.atm)	2.10 ⁻⁴	<
Dangerous substances according to the database "Dangerous substances" available on: http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm		-	-	None	-

Durability

Oxidation	Tensile strength according to EN 12311-1	Maximum strength	EN 14575	%	100	75
		Maximum elongation			100	75
Weathering	Residual value according to EN 12226	Maximum strength	EN 12224	%	100	75
		Maximum elongation			100	75