

PRODUCT DATA SHEET

COLETANCHE XP1

DESCRIPTION

COLETANCHE XP1 is an SBS elastomeric modified bituminous geomembrane.

USE

Very low level of mechanical constraints, covered with top soil, for use an environmental protection and groundworks waterproofing, in particular :

- Low water basin,
 - Ditches,
 - Landfill covers,
 - Waste tip covers, of moderate height.
- Product use must be validated by Axter.

APPLICATION METHOD

By torch welding or other similar technique

STORAGE

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 35 cm to be placed under the ends of the mandrel.

COMPOSITION

(indicative)

Reinforcement (gm/m ²) :	Geotextile	175
Binder (gm/m ²) :	Elastomeric SBS	3800
Surface finish (gm/m ²) :	Sand	250
Under surface finish (gm/m ²) :	Siliconed film	10

CHARACTERISTICS

		STANDARD	UNITS	VALUES	Min
Dimensions	Length	EN 1848-1	m	100	99
	Width		m	5,10	5,01
Thickness (on finished product)		EN 1849-1	mm	3,2	3,0
Surface mass		EN 1849-1	kg/m ²	4,30	3,90
Tensile properties : maximum tensile strength	Longitudinal	EN 12311-1	N/50 mm	950	750
	Cross direction			800	630
Tensile properties : elongation	Longitudinal	EN 12311-1	%	35	25
	Cross direction			35	25
Flexibility at low temperature		EN 1109	°C	-20	-16
Static Puncture	Resistance	EN ISO 12236	kN	2,7	2,4
	Move		mm	50	40
Water permeability (liquid tightness)		EN 14150	m ³ /m ² /j	1.10 ⁻⁶	<
Gas permeability (gas tightness)		ASTM D 1434-82	m ³ /(m ² .j.atm)	2.10 ⁻⁴	<
Dangerous substances consult : http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm		-	-	None	

Durability

Oxidation	Tensile strength according to EN 12311-1 retained tensile strength according to EN 12226	Maximum tensile strength	EN 14575	%	100	75
		Elongation			100	75
Weathering		Maximum tensile strength	EN 12224	%	100	75
		Elongation			100	75

The manufacturer reserves the right to modify, at any time, the characteristics of its products.

