

## Product data sheet

### COLETANCHE ES4

#### Description

Coletanche ES4 is an elastomeric modified bituminous geomembrane.

#### Use

Extreme level of mechanical constraints, exposed or covered (aggressive materials, reinforced precautions). For example:

- Storage of harmful waste,
- Large dams,
- Railways (use directly under ballast),
- Railway bridges.

The product use must be validated by consultation.

#### Application method

By torch welding or other similar process.

#### Storage

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 35 cm to be placed under the ends of the mandrel.

#### Composition (indicative)

Reinforcement:	Geotextile	400 g/m <sup>2</sup>
Reinforcement:	Glass fleece	50 g/m <sup>2</sup>
Binder:	Elastomeric bitumen	5400 g/m <sup>2</sup>
Surface finish:	Sand	250 g/m <sup>2</sup>
Underside finish:	Silicone coated film	15 g/m <sup>2</sup>

#### Characteristics

		Standards	Units	Average	Minimum
Dimensions	Length	-	m	55	54
	Width		m	5.10	5.01
Thickness (on finished product)		ASTM D5199	mm	5.60	4.80
Surface mass		ASTM D5261	kg/m <sup>2</sup>	6.40	5.90
Tear resistance	Longitudinal direction	ASTM D4073	N	1225	919
	Cross direction			1025	769
Tensile properties: Strength	Longitudinal direction	ASTM D7275	kN/m	35	29.2
	Cross direction			30	23.2
Tensile properties: Elongation	Longitudinal direction		%	60	45
	Cross direction			60	45
Static puncture		ASTM D4833	N	650	585
Flexibility at low temperature	Longitudinal direction	ASTM D5147	°C	-20	-15
	Cross direction			-20	-15
Water permeability		ASTM E96	m/s	6.10 <sup>-14</sup>	<
Gas permeability		ASTM D1434-82	m <sup>3</sup> /(m <sup>2</sup> .d.atm)	2.10 <sup>-4</sup>	<

The manufacturer reserves the right to modify, at any time, the characteristics of its products.