

# PRODUCT DATA SHEET

## COLETANCHE SC1

### DESCRIPTION

COLETANCHE SC1 is an SBS elastomeric modified bituminous geomembrane.  
Rolls standards dimensions are 5.05m x 140m - Other dimensions on request

### USE

Very low level of mechanical constraints, covered with top soil, no risk of puncture or tension:  
- Gutters  
- Curved Gutters  
Other product uses must be validated by Axter Coletanche® Inc

### APPLICATION METHOD

Welded joints

### STORAGE

Rolls must not be stored directly on the ground. They must be laid supported on concrete blocks, trestles or timber beams) min 50 cm height, placed under the mandrel ends.

### COMPOSITION

(indicative)

Reinforcement (g/m <sup>2</sup> ) :	Non-woven geotextile	250
Binder (g/m <sup>2</sup> ) :	Elastomeric SBS	2000
Surface finish (g/m <sup>2</sup> ) :	Sand	200
Under surface finish (g/m <sup>2</sup> ) :	Polyester	15

### CHARACTERISTICS

	STANDARD	UNITS	VALUES	Tolerance	
				Min	Max
Dimensions	-	Length	140	139	
		Width	5.05	5.00	
Thickness (on finished product)	ASTM D 5199	mm	2.20	2.00	3.00
Surface mass	ASTM D 3776	kg/m <sup>2</sup>	2.50	2.20	3.20
Resistance to tearing	ASTM D 4073	Longitudinal	600	550	
		Cross direction	550	500	
Tensile properties : maximum tensile strength	ASTM D 7275	Longitudinal	25	23	
		Cross direction	21	17	
Tensile properties : elongation	ASTM D 7275	Longitudinal	40	35	
		Cross direction	40	30	
Tensile properties : maximum tensile strength	ASTM D 4595	Longitudinal	27	24	
		Cross direction	24	20	
Tensile properties : elongation	ASTM D 4595	Longitudinal	74	60	
		Cross direction	74	60	
Static Puncture	ASTM D 4833	N	580	500	
Flexibility at low temperature	ASTM D 5147	Surface	-16		
		Under surface	-16		
Water permeability (liquid tightness)	ASTM E 96	m/s	6.10 <sup>-14</sup>		
Gas permeability (gas tightness)	ASTM D 1434	m <sup>3</sup> /(m <sup>2</sup> .j.atm)	1.024.10 <sup>-14</sup>		

NOTE: AXTER COLETANCHE INC. may modify the composition and/or utilisation of its products without prior notice. Consequently orders will be filled according to the latest specification.

The manufacturer reserves the right to modify, at any time, the characteristics of its products.

