

# PRODUCT DATA SHEET

## COLETANCHE XPC HFA

### DESCRIPTION

COLETANCHE XPC HFA is an SBS elastomeric modified bituminous geomembrane.

### USE

Very low level of mechanical constraints, covered with top soil, no risk of puncture or tension:

- Ditches,
- Culverts.

The geomembrane has the same friction angle on both sides.

Other product uses must be validated by AXTER.

### APPLICATION METHOD

By torch welding or other similar technique

### STORAGE

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 1.2 ft to be placed under the ends of the mandrel.

### COMPOSITION

(indicative)

Reinforcement (g/m <sup>2</sup> ) :	Geotextile	175
Binder (g/m <sup>2</sup> ) :	Elastomeric SBS	2100
Surface finish (g/m <sup>2</sup> ) :	Sand	250
Under surface finish (g/m <sup>2</sup> ) :	Peel-off siliconed film	40

### CHARACTERISTICS

		STANDARD	UNITS	VALUES	Min
Dimensions	Length	-	m	140	139
	Width		m	5,10	5,01
Thickness (on finished product)		ASTM D 5199	mm	2,20	2,00
Surface mass		ASTM D 3776	kg/m <sup>2</sup>	2,50	2,20
Resistance to tearing	Longitudinal	ASTM D 4073	N	600	500
	Cross direction			500	400
Tensile properties : maximum tensile strength	Longitudinal	ASTM D 7275	kN/m	19	15
	Cross direction			16	12,6
Tensile properties : elongation	Longitudinal	ASTM D 7275	%	35	25
	Cross direction			35	25
Static Puncture		ASTM D 4833	N	400	360
Flexibility at low temperature	Longitudinal	ASTM D 5147	°C	-20	-15
	Cross direction			-20	-15
Water permeability (liquid tightness)		ASTM E 96	m/s	6.10 <sup>-14</sup>	<
Gas permeability (gas tightness)		ASTM D 1434-82	m <sup>3</sup> /(m <sup>2</sup> .j.atm)	2.10 <sup>-4</sup>	<

NOTE: AXTER may modify the composition and/or utilisation of its products without prior notice. Consequently orders will be filled according to the latest specification.

