

Product data sheet

COLETANCHE ES1 HFA

Description

Coletanche ES1 HFA is an elastomeric modified bituminous geomembrane.

Use

Low level of mechanical constraints, exposed or covered limiting risks of puncture and tensile stresses. For example:

- Landfill and waste capping,
- Shallow hydraulic ponds,
- Ditches.

The membrane has the same friction angle on both sides.

The product use must be validated by consultation.

Application method

By torch welding or other similar process.

Storage

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 1.2 ft to be placed under the ends of the mandrel.

Composition (indicative)

Reinforcement:	Geotextile	5.9 oz/yd ²
Reinforcement:	Glass fleece	1.5 oz/yd ²
Binder:	Elastomeric bitumen	112.1 oz/yd ²
Surface finish:	Sand	7.4 oz/yd ²
Underside finish:	Peel-off silicone coated film	1.2 oz/yd ²

Characteristics

		Standards	Units	Average	Minimum
Dimensions	Length	-	ft	328	325
	Width		ft	16.70	16.40
Thickness (on finished product)		ASTM D5199	mil	137.80	122.00
Surface mass		ASTM D5261	oz/yd ²	123.90	109.10
Tear resistance	Longitudinal direction	ASTM D4073	lbf	169	127
	Cross direction			112	84
Tensile properties: Strength	Longitudinal direction	ASTM D7275	lbf/in	126	94
	Cross direction			103	77
Tensile properties: Elongation	Longitudinal direction		%	60	45
	Cross direction			60	45
Static puncture		ASTM D4833	lbf	101	91
Flexibility at low temperature	Longitudinal direction	ASTM D5147	°F	-4	5
	Cross direction			-4	5
Water permeability		ASTM E96	m/s	6.10 ⁻¹⁴	<
Gas permeability		ASTM D1434-82	m ³ /(m ² .d.atm)	2.10 ⁻⁴	<

The manufacturer reserves the right to modify, at any time, the characteristics of its products.