

Product data sheet

COLETANCHE SC1

Description

Coletanche SC1 is an elastomeric modified bituminous geomembrane.

Use

Very low level of mechanical constraints, covered with no risk of puncture or stress. For example:

- Gutters,
- Channels, highway and roadway ditches.

Requires cover in areas where the geomembrane can be damaged (immediate proximity to the road for example). May remain exposed in other cases.

The product use must be validated by consultation.

Application method

By torch welding or other similar process.

Storage

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 1.2 ft to be placed under the ends of the mandrel.

Composition (indicative)

Reinforcement:	Geotextile	7.4 oz/yd ²
Reinforcement:	-	-
Binder:	Elastomeric bitumen	61.9 oz/yd ²
Surface finish:	Sand	7.4 oz/yd ²
Underside finish:	Peel-off silicone coated film	0.4 oz/yd ²

Characteristics

		Standards	Units	Average	Minimum
Dimensions	Length	-	ft	459	456
	Width		ft	16.70	16.40
Thickness (on finished product)		ASTM D5199	mil	86.60	78.70
Surface mass		ASTM D5261	oz/yd ²	73.70	64.90
Tear resistance	Longitudinal direction	ASTM D4073	lbf	180	157
	Cross direction			169	146
Tensile properties: Strength	Longitudinal direction	ASTM D7275	lbf/in	148	114
	Cross direction			126	103
Tensile properties: Elongation	Longitudinal direction		%	40	30
	Cross direction			40	30
Static puncture		ASTM D4833	lbf	130	112
Flexibility at low temperature	Longitudinal direction	ASTM D5147	°F	-4	5
	Cross direction			-4	5
Water permeability		ASTM E96	m/s	6.10 ⁻¹⁴	<
Gas permeability		ASTM D1434-82	m ³ /(m ² .d.atm)	2.10 ⁻⁴	<

The manufacturer reserves the right to modify, at any time, the characteristics of its products.