

Product data sheet

COLETANCHE XP2 HFA

Description

Coletanche XP2 HFA is an elastomeric modified bituminous geomembrane.

Use

Moderate level of mechanical constraints, exposed or covered (allow hot asphalt mixes). For example:

- Landfill and waste capping, biogas barriers,
- Methanisation units, industrial platforms,
- Hydraulic, mining and industrial ponds,
- Canals.

The membrane has the same friction angle on both sides.

The product use must be validated by consultation.

Application method

By torch welding or other similar process.

Storage

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 1.2 ft to be placed under the ends of the mandrel.

Composition (indicative)

Reinforcement:	Geotextile	5.9 oz/yd ²
Reinforcement:	-	-
Binder:	Elastomeric bitumen	112.1 oz/yd ²
Surface finish:	Sand	7.4 oz/yd ²
Underside finish:	Peel-off silicone coated film	1.2 oz/yd ²

Characteristics

		Standards	Units	Average	Minimum
Dimensions	Length	-	ft	328	325
	Width		ft	16.70	16.40
Thickness (on finished product)		ASTM D5199	mil	126.00	118.10
Surface mass		ASTM D5261	oz/yd ²	126.80	115.00
Tear resistance	Longitudinal direction	ASTM D4073	lbf	146	124
	Cross direction			135	112
Tensile properties: Strength	Longitudinal direction	ASTM D7275	lbf/in	114	97
	Cross direction			103	86
Tensile properties: Elongation	Longitudinal direction		%	40	30
	Cross direction			40	30
Static puncture		ASTM D4833	lbf	110	101
Flexibility at low temperature	Longitudinal direction	ASTM D5147	°F	-4	5
	Cross direction			-4	5
Water permeability		ASTM E96	m/s	6.10 ⁻¹⁴	<
Gas permeability		ASTM D1434-82	m ³ /(m ² .d.atm)	2.10 ⁻⁴	<

The manufacturer reserves the right to modify, at any time, the characteristics of its products.