

# PRODUCT DATA SHEET

## COLETANCHE ES 1



### DESCRIPTION

COLETANCHE ES 1 is an SBS elastomeric modified bituminous geomembrane.

### USE

Very low level of mechanical constraints, covered with top soil, for use an environmental protection and groundworks waterproofing, in particular :

- Low water basin,
- Ditches,
- Landfill covers,
- Waste tip covers.

Product use must be validated by Axter.

### APPLICATION METHOD

By torch welding or other similar technique.

### STORAGE

Rolls must not be stored directly on the ground. Provide suitable supports (blocks, slides, wooden planks) with a minimum height of 1.2 ft to be placed under the ends of the mandrel.

### COMPOSITION

(indicative)

Reinforcement (oz/yd <sup>2</sup> ) :	Glass mat	1.5
Reinforcement (oz/yd <sup>2</sup> ) :	Non-woven geotextile	5.9
Binder (oz/yd <sup>2</sup> ) :	Elastomeric SBS	112.1
Surface finish (oz/yd <sup>2</sup> ) :	Sand	7.4
Under surface finish (oz/yd <sup>2</sup> ) :	Polyester	0.4

### CHARACTERISTICS

		STANDARD	UNITS	AVERAGE	Min
Dimensions	Length	-	ft	328	325
	Width		ft	16.7	16.4
Thickness (on finished product)		ASTM D 5199	mils	138	122
Mass per Unit Area		ASTM D 3776	oz/yd <sup>2</sup>	124	109
Resistance to tearing	Longitudinal	ASTM D 4073	lbf	169	127
	Cross direction			112	84
Tensile properties : maximum tensile strength	Longitudinal	ASTM D 7275	lbf/in.	126	94
	Cross direction			103	77
Tensile properties : elongation	Longitudinal	ASTM D 7275	%	60	45
	Cross direction			60	45
Static Puncture		ASTM D 4833	lbf	101	91
Flexibility at low temperature	Longitudinal	ASTM D 5147	°F	-4	5
	Cross direction			-4	5
Water permeability (liquid tightness)		ASTM E 96	m/s	6.10 <sup>-14</sup>	<
Gas permeability (gas tightness)		ASTM D 1434-82	m <sup>3</sup> /(m <sup>2</sup> .j.atm)	2.10 <sup>-4</sup>	<

NOTE: AXTER COLETANCHE INC. may modify the composition and/or utilisation of its products without prior notice. Consequently orders will be filled according to the latest specification.

